

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-129275

(43)Date of publication of application : 09.05.2000

(51)Int.Cl. C10M107/34
C09K 5/04
C10M105/18
C10M129/84
C10M137/04
F25B 1/00
// C10N 40:30

(21)Application number : 10-308387

(71)Applicant : HITACHI LTD

(22)Date of filing : 29.10.1998




(72)Inventor : OTA AKIRA
ITO YUTAKA
KAWASHIMA KENICHI
IIZUKA TADASHI

(54) WORKING FLUID COMPOSITION FOR REFRIGERATING/AIR- CONDITIONING MACHINE AND REFRIGERATING/AIR-CONDITIONING APPARATUS USING SAME

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a working fluid composition which can prevent the viscosity decrease of a refrigerant/refrigerator oil mixture and the lubrication defects of a compressor by incorporating a refrigerant comprising propane and/or isobutane together with a polyalkylene glycol into the same.

SOLUTION: The polyalkylene glycol is represented by formula I (wherein R1 is H or 1-4C alkyl; R3 to R6 are each H or CH3; X is 2-4C oxyalkylene; and (m), (n), (p), and (q) are each 1-30 provided when X is not present, then (p) and (q) are both 0). Preferably, 0.05-5.0 wt.% phosphorus compound represented by formula II or 0.05-5.0 wt.% cyclic carbonate compound represented by formula III is added to the polyalkylene glycol. In these formulas, R7 is 4-18C alkyl, oleyl, phenyl, or o-, m-, or p-tolyl; and R8 is H, or 1-4C (perfluoro)alkyl. In addition, the composition can improve the pull down (cool down) properties of a refrigerating/air-conditioning apparatus.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision
of rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office